



Technical Data Sheet

AEROWAX™ HT Wax Maskant

Product Description

AEROWAX HT Wax Maskant is a highly refined platers wax with a melting point range of 180-190 °F (82-88 °C). It effectively masks both simple and complex geometries and is suitable for hard chrome, nickel sulfamate and other selective plating operations.

Features and Benefits

- Resists Crazing and Cracking
- Excellent Adhesion and Flexibility
- High Temperature Stability
- Resistant to Harsh Plating Chemicals
- Detectable Under UV Light
- Easily Removed using Vantage™ Cleaning Agents

Properties

Form	Slabs
Melting Point Range	180-190 °F (82-88 °C)
Needle Penetration (25 °C)	~18 dmm
Viscosity (100 °C)	16.5-21 mm ² /s

Process

Add **AEROWAX HT** to the tank reservoir(s) and apply heat.

Two (2) Tank Operation (Apply a minimum of two coats of wax)

1. For good adhesion, heat the 1st tank to 245 °F ± 15 °F (118 °C ± 9 °C).
2. Immerse a clean dry part in the wax bath until it reaches the temperature of the wax bath. Remove and cool slightly.
3. For subsequent coatings, heat the 2nd tank to ~200 °F (93 °C).
4. Dip part in bath and withdraw quickly, allowing to cool slightly.
5. Repeat until part has desired wax coating thickness.

1 Tank Operation (Apply a minimum of two coats of wax)

1. Heat the tank to 230 °F ± 10 °F (110 °C ± 5 °C).
2. Immerse a clean dry part in the wax bath until it reaches the temperature of the wax bath. Remove part and cool slightly.
3. For subsequent coatings, dip part in the same tank and withdraw quickly. Allow to cool slightly.
4. Repeat until part has desired wax coating thickness.

Removal

Easily removed by Petroferm BIOACT® 280 series dewaxing agents.

Disposal/Safety

Disposal

Vantage recommends contacting your current or local environmental service company for proper disposal.

Safety

Please see Safety Data Sheet for further information.



Technical Data Sheet

AEROWAX™ HT Wax Maskant

Packaging

Available in 60 lb (27 kg) cartons.

Shelf Life

36 months when stored in original, sealed container above 50 °F (10 °C)



ISO 9001:2008



RoHS
Compliant



LEAD FREE



HALOGEN
FREE



SVHC
REACH ✓

AEROWAX is a trademark of Vantage Specialties, Inc. BIOACT is a registered trademark of Vantage Specialties, Inc.

Typical property data is not intended for specification purposes. Vantage Specialties, Inc., its sales agents and distributors make no warranty of merchantability of the product or of product fitness for any particular purpose. This product and all information supplied are used at the purchaser's own risk. The purchaser assumes all risk of use or handling of the product, whether in accordance with directions or not.

Vantage Specialties, Inc.

3938 Porett Drive • Gurnee, Illinois 60031 USA • P +1 847 244 3410 • F +1 847 249 6346 • www.vantagegrp.com